

Mechanical	Imperial	Metric
Ultimate Tensile Strength	8300 psi	57 MPa
Ultimate Tensile Elongation	4%	4%
Tensile Modulus	290 ksi	2000 MPa
Flexural Strength	13100 psi	90 MPa
Flexural Modulus	310 ksi	2100 MPa
Izod Impact, Notched	1.6 ft-lb/in	86 J/m
Izod Impact, Un-notched	1 ft-lb/in	53 J/m
Thermal	Imperial	Metric
Heat Deflection Temperature @ 66 psi	271°F	133°C
Heat Deflection Temperature @ 254 psi	260°F	127°C
Vicat Softening Temperature	282°F	139°C
Glass Transition Temperature	322°F	161°C
Melting Point	n/a	n/a
Electrical		
Volume Resistivity	1.5E14 - 8.0E13 ohm-cm	
Dielectric Constant	2.8 - 3.0	
Dissipation Factor	0.0009 - 0.0005	
Dielectric Strength	370 - 70 V/mil	
Other		
Specific Gravity	1.2	
Flame Classification	HB	